

420

Martensitic stainless steel that provides great corrosion resistance with increased strength and hardness

Key Features:

- > Excellent hardness
- > Good abrasive resistance
- > Great corrosion resistance
- > Good processibility by laser sintering technology

Example Applications:

- > Medical instruments for surgical and dental use
- > Versatile use for many tooling construction
- > Versatile use for many industrial applications including valves, gears, shafts, cams, pivots etc.
- > Industrial components fabrication used at moderately elevated temperatures

[Technical Data]

General Properties	Part Density <small>ISO3369</small>	≥7.70 g/cm ³
Mechanical Properties ¹ (Heat treated)	Tensile Strength <small>ISO6892-1</small>	≥ 1700 MPa
	Yield Strength <small>ISO6892-1</small>	≥ 700 MPa
	Elongation after Fracture <small>ISO6892-1</small>	≥ 5 %
	Vickers hardness <small>ISO6507-1 / ISO6508-1</small>	≥ 48 HRC

¹ For more information on heat treatment process, please contact us directly. Farsoon systems are open material platform. For special materials such as tungsten, tantalum and pure copper, please contact us with your inquiries or requirements.

Disclaimer: Many factors may affect the performance characteristics of products. We recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. Farsoon makes no warranties of any type, express or implied, including but not limited to, the warranties of merchantability or fitness for a particular use. This also applies regarding the consideration of possible intellectual property rights as well as laws and regulations. Farsoon reserves the right to change the technical data without notice. Farsoon®, Buildstar®, Makestar® are registered trademarks of Farsoon Technologies. Last Change: 2024-09



Mold Insert Component
System: FS121M

www.farsoon.com