

Maraging Steel Grade 300

Genuine tool steel 18Ni300 offering superior strength and toughness

Key Features:

- > Excellent and stable mechanical properties
- > High strength and hardness
- > Easily heat-treatable and machinable to obtain required hardness & strength

Example Applications:

- > Producing a variety types of tools and molds
- > Great choice for manufacturing of plastic injection molds with internal cooling channels
- > High-performance parts in aerospace and automotive engineering

[Technical Data]

General Properties

Part Density ISO3369 $\geq 8.00 \text{ g/cm}^3$

Mechanical Properties ¹

(Heat treated)

Tensile Strength ISO6892-1 $\geq 1800 \text{ MPa}$

Yield Strength ISO6892-1 $\geq 1700 \text{ MPa}$


Elongation after Fracture ISO6892-1 $\geq 6 \%$

Vickers hardness ISO6507-1 / ISO6508-1 $\geq 48 \text{ HV5/15}$

¹ For more information on heat treatment process, please contact us directly.

Farsoon systems are open material platform. For special materials such as tungsten, tantalum and pure copper, please contact us with your inquiries or requirements.

Disclaimer: Many factors may affect the performance characteristics of products. We recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. Farsoon makes no warranties of any type, express or implied, including but not limited to, the warranties of merchantability or fitness for a particular use. This also applies regarding the consideration of possible intellectual property rights as well as laws and regulations. Farsoon reserves the right to change the technical data without notice. Farsoon®, Buildstar®, Makestar® are registered trademarks of Farsoon Technologies. Last Change: 2024-09



Conformal Cooling Mold
 System: FS273M
 Partner: Oerlikon

www.farsoon.com